

CHEMICAL HOUSE

PTY. LTD.

A.C.N. 010 418 589

9 Production Avenue,
Ernest, Qld. 4214

P.O. Box 595 ASHMORE CITY, Qld. 4214

Phone: 07) 5594 0344
Fax: 07) 5594 0236

PRODUCT:

TOPCOAT ACRYLIC SEALER

NSC

Natural Stone & Concrete Care

DESCRIPTION:

TOPCOAT ACRYLIC SEALER is an acrylic solvent based system, designed to be used as a 7 day sealer on **TOPCOAT SPRAY SYSTEM** (Spray on Stencil), Stencil, Stamped Concrete, Garden Edging, Exposed Aggregate etc. **TOPCOAT ACRYLIC SEALER** contains selected additives, which reduce hot tyre marking, reducing the problematic marring and scuffing of the sealer. **TOPCOAT ACRYLIC SEALER** should be applied to the surface with a low pressure spray, roller, brush or natural hair broom, use of nylon, polyethylene or other plastics will result in their dissolution. **TOPCOAT ACRYLIC SEALER** is designed to give a wet look gloss finish, however the result will be very dependent on the porosity of the surface to be sealed. Always apply two- (2) coats minimum. **TOPCOAT ACRYLIC SEALER** has a higher solids level than **HD LOCKWEAR, & PAVE SEAL** and solvent ratios and is not the same.

SURFACE PREPERATION:

Areas to be treated must be clean, free from oil & grease, including surface curing compounds. A light acid etch (see "Acid Etching of Concrete" information sheet) on most cementaceous surfaces prior to coating is recommended, to ensure no unreacted laitance is present, when applying to new stamped, exposed aggregate concrete.

DIRECTIONS FOR USE :

Apply **TOPCOAT ACRYLIC SEALER** with a Spray, lambs wool roller or broom. Do not apply on new concrete as shrinkage of the concrete during the drying process may result in delamination of the sealer and subsequent whitening if the surface. Wait 7 days prior to coating with **TOPCOAT ACRYLIC SEALER**. Allow **TOPCOAT ACRYLIC SEALER** at least 24 hours full dry before light traffic is permitted on surface. Apply on the surface to be sealed, coating in one general direction (i.e. north-south). Re-coat when first coat dry, across the direction of the first coat (i.e. east-west) to ensure complete coverage.

Do not apply in temperatures below 5°C or above 30°C as blooming or bubbling of the coating may occur.

COVERAGE

An average expected figure is 2-5m²/L.

CLEAN-UP

Wash up with Xylene.

Properties

Resin type	acrylic
NVM %	25%
Specific Gravity	0.91
Viscosity	100-220cps

FIRST AID, SAFETY & STORAGE

Refer to Material Safety Data sheet. These are available on request.

PACKS:

10L, 20L & 200L.

Ref:Topcoat_Acr_pds
Date: Aug 04